

TELCO – Distinct Advantage of Being 90% Machinable

Specification	Free Cutting Brass	Hard Drawn Copper	Telco
Relative Machinability Rating	100%	20%	90%
Electrical Conductivity	26%	100%	90%
Density (lbs. per cu. in.)	.307	.323	.323
Approx. Wear Ratio into Steel	1:01	2:01	2:01